




粗大結晶粒(低保磁力)が角形性低下の一因

試料	日系Nd磁石	外国製Nd磁石A	外国製Nd磁石B
SEM画像			
最大粒子径 (μm)	9.250	12.950	19.010
最小粒子径 (μm)	3.410	4.720	4.960
平均粒子径 (μm)	6.112	8.877	8.704
標準偏差	1.782	2.487	3.702

粗大結晶粒

保磁力大



保磁力小